

| | 1 | error | 2 | error | 3 | error | 4 | error | 5 | error |
|---------------|---------|-------|--------|-------|--------------|-------|--------------|-------|--------|-------|
| | エジリン? | | スギライト? | | 片山石? (バラトフ石) | | 片山石? (バラトフ石) | | 村上石? | |
| Nb (ネオジム) | 0.002 | 0.001 | | 0.000 | | 0.000 | | 0.000 | | 0.000 |
| Zr (ジルコニウム) | 0.041 | 0.001 | 0.007 | 0.001 | 0.005 | 0.001 | 0.002 | 0.001 | 0.021 | 0.001 |
| Sr (ストロンチウム) | 0.003 | 0.001 | | 0.000 | | 0.000 | | 0.000 | | 0.000 |
| Bi (ビスマス) | 0.003 | 0.001 | | 0.000 | | 0.000 | | 0.000 | | 0.000 |
| Zn (亜鉛) | 0.010 | 0.002 | | 0.000 | | 0.000 | | 0.000 | | 0.000 |
| Fe (鉄) | 4.271 | 0.054 | 0.536 | 0.021 | 0.429 | 0.019 | 0.376 | 0.018 | 0.804 | 0.026 |
| Mn (マンガン) | 0.077 | 0.011 | | 0.000 | | 0.000 | | 0.000 | | 0.000 |
| Cr (クロム) | 0.016 | 0.001 | | 0.000 | 0.004 | 0.001 | | 0.000 | 0.002 | 0.001 |
| V (バナジウム) | 0.007 | 0.001 | | 0.000 | | 0.000 | | 0.000 | 0.005 | 0.001 |
| Ti (チタン) | 0.057 | 0.002 | 0.014 | 0.001 | 0.008 | 0.001 | | 0.000 | 0.055 | 0.002 |
| Ca (カルシウム) | 2.484 | 0.035 | 0.464 | 0.012 | 0.954 | 0.018 | 0.108 | 0.005 | 1.054 | 0.020 |
| K (カリウム) | 0.347 | 0.010 | 0.126 | 0.007 | 0.138 | 0.007 | 0.114 | 0.006 | 0.329 | 0.009 |
| Al (アルミニウム) | 4.581 | 0.061 | 4.918 | 0.069 | 5.713 | 0.083 | 5.742 | 0.081 | 5.623 | 0.085 |
| P (リン) | 0.048 | 0.006 | 0.029 | 0.006 | 0.020 | 0.007 | 0.037 | 0.007 | 0.044 | 0.008 |
| Si (シリカ) | 28.866 | 0.191 | 28.174 | 0.257 | 30.339 | 0.261 | 29.819 | 0.266 | 30.127 | 0.270 |
| S (硫黄) | 0.061 | 0.002 | 0.037 | 0.002 | 0.040 | 0.003 | 0.023 | 0.002 | 0.018 | 0.002 |
| Mg (マグネシウム) | 0.157 | 0.049 | | 0.000 | | 0.000 | | 0.000 | | 0.000 |
| Bal (その他軽い元素) | 58.970 | 0.293 | 65.691 | 0.324 | 62.346 | 0.338 | 63.778 | 0.334 | 61.866 | 0.356 |
| total | 100.001 | | 99.996 | | 99.996 | 0.739 | | | 99.948 | |



▼使用機器

メーカー名；Thermo Fisher
商品名/型式；iton XL3t-950S



▲試験体